

Test Report

REPORT NO:

UG/2020/40265A-01

Date: 2020/04/27

Page : 1 of 3



TOP COLOUR FILM LTD.

NO.69, DINGHN RD., GUISHAN DIST., TAOYUAN CITY 33378, TAIWAN

The following sample(s) was/were submitted and identified by/on behalf of applicant as:

Sample Name : Anti-Bacteria Safety Film
Applicant : TOP COLOUR FILM LTD.
Address of Applicant : NO.69, DINGHN RD., GUISHAN DIST., TAOYUAN CITY 33378, TAIWAN
Tel No./Contact Person : 03-3288840 / Edward Wang
Packaging Condition : Please refer to the photo for sample shown at the last page of this report.
Quantity : 6pcs
Storage Condition : Room temperature
Item No. : BRC S100
Lot/Batch No. : 2020001
Manufacturer/Agent/Importer : TOP COLOUR FILM LTD.
Date of Manufacturing : 2020/3/4
Date of Expiry : 10Years
Date of Sample Received : 2020/04/06
Date of Testing : 2020/04/06 ~ 2020/04/27
Test Requested: Antimicrobial Effectiveness Testing.
Test Method : With reference to JIS Z2801-Antimicrobial products-Test for antimicrobial activity and efficacy Testing.
Test Results: -Please refer to next page(s)-

Shin Jyh Chen
Shin-Jyh Chen, Manager
Signed for and on behalf of
SGS Taiwan Ltd.



Test Report

REPORT NO:

UG/2020/40265A-01

Date: 2020/04/27

Page : 2 of 3



TOP COLOUR FILM LTD.

NO.69, DINGHN RD., GUISHAN DIST., TAOYUAN CITY 33378, TAIWAN

Test Results:

Contact Time: 24 hours

Organism	Average of the number of viable cells of bacteria on blank sample after 24 hours (CFU/cm ²)	Log average of the number of viable cells of bacteria on blank sample after 24 hours	Average of the number of viable cells of bacteria on test sample after 24 hours (CFU/cm ²)	Log average of the number of viable cells of bacteria on test sample after 24 hours	Antibacterial Activity (R)
<i>Escherichia coli</i>	1.6 × 10 ⁵	5.21	<1	0.00	5.21

NOTE :

- The test report merely reflects the test results of the consigned matters of the client and is not a certification of the legitimacy of the related products.
- All items in this testing report is based on the request from client and we are responsible for that.
- The content of this report is invalid if it is not presented as the entire report.
- Organism No.:
Escherichia coli BCRC 11634 ; ATCC 8739
- Antibacterial Activity(R)= (Log average of the number of viable cells of bacteria on blank sample after 24 hours – Log number of viable cells of bacteria on test sample after 24 hours)
- R shall be ≥ 2.0 for Antibacterial effectiveness.

- END -

Test Report

REPORT NO:

UG/2020/40265A-01

Date: 2020/04/27

Page : 3 of 3



TOP COLOUR FILM LTD.

NO.69, DINGHN RD., GUISHAN DIST., TAOYUAN CITY 33378, TAIWAN

Sample Photo

UG/2020/40265



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.