

**TOP COLOUR**  
Window Film

**SP 204**

Construction 1 ply - 1mil  
2 ply - 1.5mil Available

Visible Light Transmitted (380nm~780nm)		5%
Visible Light Reflected	External	4.5%
	Internal	5%
Solar Heat	Transmitted	31%
	Reflected	5%
	Absorbed	64%
IR Reduction (900nm~1100nm)		42%
UV Rejected (290nm~400nm)		99.90%
Total Solar Energy Rejected (TSER)		47%
Shading Coefficient (S.C.)		0.61
Solar Heat Coefficient (SHGC)		0.53
Scratch Resistant		>2H

Test, equipment and methods are in accordance with Lens Tester Q-2401, P.D. 2.1 and UV-VIS SPM UV-2600. Performances results were generated from testing film applied to 1/8" (3mm) clear glass. This data is provided for information purposes only.

**TOP COLOUR**  
Window Film

**SP 205**

Construction 1 ply - 1mil  
2 ply - 1.5mil Available

Visible Light Transmitted (380nm~780nm)		13%
Visible Light Reflected	External	4.5%
	Internal	5%
Solar Heat	Transmitted	40%
	Reflected	5%
	Absorbed	55%
IR Reduction (900nm~1100nm)		32%
UV Rejected (290nm~400nm)		99.90%
Total Solar Energy Rejected (TSER)		41%
Shading Coefficient (S.C.)		0.67
Solar Heat Coefficient (SHGC)		0.59
Scratch Resistant		>2H

Test, equipment and methods are in accordance with Lens Tester Q-2401, P.D. 2.1 and UV-VIS SPM UV-2600. Performances results were generated from testing film applied to 1/8" (3mm) clear glass. This data is provided for information purposes only.

**TOP COLOUR**  
Window Film

**SP 206**

Construction 1 ply - 1mil  
2 ply - 1.5mil Available

Visible Light Transmitted (380nm~780nm)		37%
Visible Light Reflected	External	5%
	Internal	6%
Solar Heat	Transmitted	57%
	Reflected	6%
	Absorbed	37%
IR Reduction (900nm~1100nm)		21%
UV Rejected (290nm~400nm)		99.00%
Total Solar Energy Rejected (TSER)		30%
Shading Coefficient (S.C.)		0.80
Solar Heat Coefficient (SHGC)		0.70
Scratch Resistant		>2H

Test, equipment and methods are in accordance with Lens Tester Q-2401, P.D. 2.1 and UV-VIS SPM UV-2600. Performances results were generated from testing film applied to 1/8" (3mm) clear glass. This data is provided for information purposes only.