

TOP COLOUR

Window Film

SP 919

Construction 2 ply - 1.8mil

Visible Light Transmitted (380nm~780nm)		1%
Visible Light Reflected	External	32%
	Internal	4.5%
Solar Heat	Transmitted	9%
	Reflected	33%
	Absorbed	58%
IR Reduction (900nm~1100nm)		82%
UV Rejected (290nm~400nm)		99.99%
Total Solar Energy Rejected (TSER)		71%
Shading Coefficient (S.C.)		0.33
Solar Heat Coefficient (SHGC)		0.29
Scratch Resistant		>2H

Test, equipment and methods are in accordance with Lens Tester Q-2401, P.D. 2.1 and UV-VIS SPM UV-2600. Performances results were generated from testing film applied to 1/8" (3mm) clear glass.

This data is provided for information purposes only.